Textiles F.R. Limited



Flame Retardancy Finishers & Consultants

Unit 4B, (30) Wharfedale Road **Euroway Trading Estate** Bradford West Yorkshire BD4 6SG

Tel: 01274 651230 Fax: 01274 651305

E-mail: sales@textilesfr.co.uk Web site: www.textilesfr.co.uk



Date 16/05/2019

Test Report & Certificate

UKAS TESTING LABORATORY No.1413

Page 1 of 1 British Standard Flammability Test Document: 21434

Test Method : BS EN ISO 15025:2002

Contract Curtain Test Specification: BS5867-2:2008:Type B

Order Details Customer Account: BAN008

TFR Order No : 253282 BANNER WORLD : EMAIL JL Customer Order UNIT 5 : 08/05/2019 Order Date BROOKSIDE CENTRE

Fabric Description : POLYESTER 210GSM RED MARSH IND ESTATE

Fabric Composition : THORNTON-CLEVELEYS

Quantity (metres) : 1.0 FY5 4HD

: Test specimens were conditioned in an atmosphere having a temperature of Sample Conditioning 20'C +/- 2'C and Relative Humidity 65% +/- 5 %

for a minimum of 24 hours prior to testing.

Relative Humidity 65 % : Temperature 20 'C Test Enclosure Conditions

: Flammability testing was performed without the durability requirements Cleansing Procedure

: stated in Section 5 of BS5867-2:2008 being completed. Other Details

: Sample tested in an as received state Sample Treatment

Report Notes: Test Procedure: This test was carried out in accordance with BSEN ISO 15025 Six specimens were prepared each measuring 200mm +/- 2mm x 160mm +/- 2mm, three with the longer Procedure A. The results may not apply to situations where dimension in the length and three with the longer there is a restricted air supply or prolonged exposure to dimension in the width. A butane flame was applied large sources of heat such as in a conflagration. to the sample face for 15 seconds.

OBSERVATIONS	Warp Direction			Weft Direction		
	10 mg/c		Rep3	Rep1	Rep2	Rep3
Flame reached an edge	No	No	No	No	No	No
Hole reached an edge	No	No	No	No	No	No
Flaming debris	No	No	No	No	No	No

Comments:

Conducted by : Mr.R. BERRY

COMPLIANCE REQUIREMENTS: No part of any hole nor any part of the lowest boundary of any flame shall reach the upper edge or either vertical edge of any specimen and there shall be no separation of flaming debris from any specimen.

The sample complied with the requirements for BS5867-2:2008:Type B Flammability testing was performed without the durability requirements

stated in Section 5 of BS5867-2,2008 being completed.

Laboratory Technician Date 16/05/2019 Authorised by: Miss K. BUTTON